



MATERIAL SPECIFICATION

Grade: X-376
Type: Cork composition
Binder: Polymeric
Granule: 12/20

PHYSICAL CHARACTERISTICS

Density (lbs/ft ³)	11 min.
Tensile Strength (psi)	80 min.
Compression (% @ 100 psi)	20 – 35 %
Recovery	75 % min.
Flexibility (5x thickness)	No cracks

FLAMABILITY

ASTM E-84 Tunnel Test	Class B
Rating	70
Smoke Developed	65
Flame Spread	

TEST METHODS

ASTM F-104 standard text methods